


AUDIMUTE FABRIC ACOUSTIC CEILING CLOUD

Frequency (Hz)	Absorption Coefficient
100	0.23
125	0.22
160	0.30
200	0.47
250	0.66
315	0.90
400	1.07
500	1.12
630	1.18
800	1.15
1000	1.10
1250	1.10
1600	1.07
2000	1.07
2500	1.06
3150	1.07
4000	1.11
5000	1.15



TEST Report Audimute Fabric Acoustic Ceiling Cloud

The test report quotes the frequency dependent sound absorption data as well as the single number ratings. Data taken from Test Report RAL-A10-005 conducted by Riverbank Acoustical Laboratories. Complete test results are available upon request.